



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND



# CWG GROUT

## Description

CWG GROUT is a dry pre-blended grout consisting of a blend of natural cement based binder, special dried & graded aggregates and retarders that is resistant to chloride penetration.

## Uses

- Waterproof grout
- Grouting during repairs to sewers
- Controlled soil stabilisation grouting
- Void filling
- Work around the sea
- Wherever pollution or chemical attack is likely.

## Properties

- Excellent adhesion
- Low shrinkage
- Excellent resistance to pure water & sulphated water
- Excellent resistance to aggressive chemicals
- Very good cohesion & mixing
- Fine compact surface
- No curing membrane necessary
- Can be used in wet conditions
- Can be used under water
- Controlled setting
- Fine particle size for greater penetration
- Set down to zero
- Can be used in contact with potable water
- Can be injected in to artesian water bearing strata, as it contains no material to leach out into the aquifer.





# CWG GROUT

## Method of use

### Preparing the surface

Do not use on frozen or over heated substrates (outside the range of 0°C-30°C).

### Mixing

For optimum results mix using conventional mixing machines.

## Application

### General

Place the material as quickly as possible after mixing using traditional methods. Once setting has started DO NOT attempt to remix, as this will cause the mechanical properties in particular strength and adhesion to be lost.

### Setting times

CWG GROUT is designed to commence setting at 35 minutes and finish setting at 45 minutes at 20°C. In winter CWG GROUT can be used down to 0°C. The set will be slower but can be accelerated by using warm water. In very hot temperatures the set will be faster and can be slowed by using cold water.

### Cleaning

CWG GROUT should be removed from tools and equipment with water immediately after use.

### Storage

CWG GROUT is packaged in a polythene inner bag re-sealable tie with a stitch sealed woven polypropylene outer bag that should be stored in dry conditions and will last for at least twelve months.

### Yield

Mixed with 4 litres of water a 25kg bag will produce approximately 10 litres of finished grout.

### How to specify

CWG GROUT shall be mixed and used all strictly in accordance with the manufacturer's instructions.

### Precautions

We strongly recommend the use of GLOVES, GOGGLES and MASK. Please see MSDS sheet for full details.

### Setting time & strength gain at 50% relative humidity

	Start Set	End Set
5°C	60 Min	65 Min
15°C	40 Min	55 Min
20°C	35 Min	45 Min

### Based on a water cement ratio of 40%

Start Set End Set	35 Min 45 Min	at 20°C at 20°C
		Compressive Strength (Mpa)
3 Days		12
7 Days		15
14 Days		17.50
21 Days		18.50
Strength continues to develop thereafter.		



Part financed by the European Community European Regional Development Fund and managed by Yorkshire Enterprise

**Distributed by:**



15 Fountain Parade, Mapplewell, Barnsley, South Yorkshire S75 6FW  
**e.** [enquiries@naturalcement.co.uk](mailto:enquiries@naturalcement.co.uk) **t.** 01226 381133 **f.** 01226 381177  
**[www.naturalcement.co.uk](http://www.naturalcement.co.uk)**