

ESMALTE AL AGUA ECOBARP METALIZADO SATINADO



Product Description

High quality acrylic enamel and special acrylic resins and hard-wearing metallic pigments based decoration.

Carta de Colores

[Carta de colores Esmaltes Metalizados Satinado Agua y Oxifer](#)



Technical Characteristics

Colour	Aluminium and colours as per chart
Appearance	Satin
Touch-dry	30-60 minutes, depending on the thickness applied and atmospheric conditions
Repainting	After 6 hours
Yield	10 - 13 m ² /l, coat, depending on conditions of surface
Thinner	Water
Storage	Excellent for up to 1 year/s, unopened, in original packaging, at normal temperature and humidity. Store in places protected against frost.

Properties

- Easy to apply
- Excellent levelling
- Non-drip
- Filling power
- Good covering power.
- Finish hard-wearing, adherent, fine and soft
- Resistant to rubbing, wear and washing
- Unchangeable colours
- Half aqueous composition
- Minimum odour
- Environmentally friendly

Applications

Suitable for decorate and protect indoor surfaces such as: Doors, radiators, walls, plaster ceilings, coving and in the home, schools, hotels, etc....., for general decoration and with metallised finish

Method of Use

Stir the contents of the pot well
Apply in thin, even, well-spread coats
A round brush, spray gun and roller: as supplied in the container or slightly diluted with water.

Preparation of surfaces

On unpainted surfaces: Sandpaper, clean and eliminate dust, grease, oil, rust, waxes, minor faults, etc...
Apply the following preparations:
On wood and plaster apply TAPAPOROS AL AGUA ECOBARP o IMPRIMACION SELLADORA BLANCO
On iron and steel apply MINIO ECOBARP AL AGUA o IMPRIMACION ANTIOXIDANTE BLANCO
On galvanised and light metals apply IMPRIMACION MULTI-USO ECOBARP AL AGUA BLANCO o IMPRIMACION MULTI-ADHERENTE BLANCO

On plaster interiors and plaster surfaces: Seal properly with SELLAFOND FIJADOR AL AGUA
Apply: 2 ó 3 coats with drying time between applications
On with old paintwork surfaces: Remove damaged paintwork and proceed as for unpainted surfaces

Other data

Packaging 0.375L, 0.750L, 4L, 20L

Remarks

Shake contents of containers before use.
For toxicological standards, consult FICHA DE SEGURIDAD.
Do not store opened or started containers.
Apply with good air renewal.

This sheet has been created with informational purposes only and does not replace expert advice. The information provided reflects our current knowledge and have been obtained from our own experience, but under no circumstance do they entail any warranty whatsoever from our part. For this reason, we cannot accept any undesired consequence deriving from its use. 26-02-2013 This sheet replaces all previous versions.