



New Guard Coatings Group

□ A global reputation to protect.

You have acquired this data sheet from the New Guard Coatings Group.

All information listed is correct at the time of print.



uksales@newguardcoatings.com



+44 1937 586311

www.newguardcoatings.com

Global Head Office: New Guard Coatings Ltd, Sandbeck Way, Wetherby, Leeds, LS22 7DN



RUST-OLEUM®
INDUSTRIAL



ND14 CLEANER/DEGREASER

Concentrated alkaline cleaner and degreaser

- Removes grease, oil, proteins, dirt and other contaminants from coated, mineral and metal substrates
- Concentrated formulation can be diluted 1:20
- Use as additive for high pressure cleaning
- Non-flammable, virtually odour-free

KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

ND14 CLEANER/DEGREASER

DESCRIPTION

Concentrated, alkaline, non-flammable, virtually odour free cleaning and degreasing solution for 100 m²/l.

RECOMMENDED USE

ND14 Cleaner/Degreaser should be used to remove grease, oil, proteins, dirt and many other surface contaminants from coated, mineral and steel substrates. Apply with an artificial sponge, cloth or stiff nylon brush or broom. Can also be used as an additive for high pressure (steam) cleaning.

THEORETICAL CONSUMPTION

The content of the concentrated 5 litre packaging will allow you to treat a surface of up to 500 m², based on a dilution of 1:20.

PRACTICAL CONSUMPTION

Practical usage depends on many factors such as type and amount of contaminants, shape of the substrate and material losses during application.

DIRECTIONS FOR USE

To ensure homogeneity shake well before use. Scrape or sweep away grease, oil, dirt, mould and all other surface contaminations as much as possible. ND14 Cleaner/Degreaser can be applied diluted or concentrated with a sponge, cloth, brush or broom. For normal cleaning a 3 - 5% concentration will be sufficient. The product should be diluted with cold water. After use rinse with plenty of fresh water. If a concentration of more than 5% is used, hot water rinsing is absolutely necessary. As a high-pressure(steam)cleaning additive a 2% concentration is recommended. After cleaning, remove any remaining water and allow the surface to dry, as moisture left on the surface or entrapped into pores may cause premature failure of the coating system. Large surface areas or poor drying conditions may require longer drying times before a coating system can be applied.

APPLICATION CONDITIONS

Temperature of air, substrate and material between 5 and 35°C.

REMARKS

If used on galvanized steel, zinc, aluminum or anodized aluminum rinse the surface excessively.

SAFETY DATA

VOC level: 92 g/l
Remarks regarding safety: Consult Safety Data Sheet and Safety Information printed on the can.

PH

12.0000

SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 27/05/2020

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu