



New Guard Coatings Group

- A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

RUST-OLEUM®
INDUSTRIAL



5800 EPOXY RAPID WB

Rapid curing water-based epoxy

- Durable epoxy floor
- Can be recoated after just 3 hours
- Available in matt or gloss finish
- Water-based, very low odour
- Excellent flow and smooth finish



KNOW-HOW TO PROTECT™

WWW.RUST-OLEUM.EU

5800 EPOXY RAPID WB

DESCRIPTION

Rapid curing epoxy floor paint for inside use. For garages, warehouses, showrooms, corridors, indoor car parks, workshops etc.

RECOMMENDED USE

5800 Epoxy Rapid WB can be applied on cleaned, sound mineral substrates, sound and well prepared previous coatings. The product can be applied directly on porous substrates; a special primer is not needed.

TECHNICAL DATA

Density:	1,2
Gloss Level:	Gloss, Matt
Solids content in volume:	48 %
Mixing Ratio:	Base : Activator = 2 : 3 (Volume)

DRYING TIMES AT 20°C/RH 50%

Touch dry:	2 hours
Dry to handle:	3 hours
Dry to recoat:	After 3 hours, within 5 days
Fully cured:	7 days (traffic possible after 24 hours)
Pot Life:	2 hours

RECOMMENDED WET FILM THICKNESS

167 µm

RECOMMENDED DRY FILM THICKNESS

80 µm

THEORETICAL CONSUMPTION

6 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Concrete must be at least 30 days old, completely dry and free of surface laitance, contaminants and previous poorly bonded coatings. Remove grease, oil and all other surface contaminations by alkaline or high pressure (steam) cleaning in combination with appropriate detergents. Sand previous coatings which are in good condition to remove gloss and to roughen the surface slightly, check compatibility. Very smooth concrete or concrete with surface laitance (a weak dusty layer) should be abraded or etched with Surfa-Etch 108 to ensure adequate adhesion. The concrete should be thoroughly washed down and allowed to dry after. Powerfloat Epoxy Floor Primer 3366 is recommended on powerfloated surfaces.

DIRECTIONS FOR USE

Stir base thoroughly before adding it to the activator. Again stir the mixture thoroughly until an even colour and consistency are obtained. Do not mix more material than can be applied in 2 hours.

Higher temperatures will reduce the pot life.

APPLICATION CONDITIONS

Apply only if the temperature of the surface and environment is between 10 and 30 °C and relative humidity is below 85%.

APPLICATION & THINNING: BRUSH

Use natural bristles, long hair brushes.

APPLICATION & THINNING: ROLLER

Apply with a medium pile simulated sheepskin roller, working well into the surface of the concrete. Thin if required with water, the product will darken slightly as curing commences and it should not be over rolled.

CLEANING OF EQUIPMENT / SPILLS

Immediately after use with warm soapy water.

REMARKS

For a glossy finish mix the base component with 5801 Epoxy Rapid Activator Gloss.

For a matt finish mix the base component with 5802 Epoxy Rapid Activator Matt.

If the product is used outside it is required to finish with a Polyurethane Topcoat such as Rust-O-Thane 9200 (do not use a clear coat).

SAFETY DATA

VOC level:	65 g/l
VOC readymix:	65 g/l
VOC category:	A/j
VOC limit:	140 g/l
Grenelle:	A+
Flashpoint:	Not flammable
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

2 year from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 15° and 25°C.

Keep from freezing.

Date issued: 25/04/2018

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T: +31 (0) 165 593 636
F: +31 (0) 165 593 600
info@rust-oleum.eu

Rust-Oleum UK Ltd.
PO Box 261
Chester-le-Street
DH3 9EH United Kingdom
T: +44 (0)1914 113 146
F: +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
11, rue Jules Verne - B.P. 60039
95322 St-Leu-La-Forêt Cedex
France
T: +33(0) 130 40 00 44
F: +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T: +32 (0) 13 460 200
F: +32 (0) 13 460 201
info@rust-oleum.eu