



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

# NOVAGUARD™ 840

## DESCRIPTION

Two-component, solvent-free, amine-cured novolac phenolic epoxy coating

## PRINCIPAL CHARACTERISTICS

- Suitable for heavy H<sub>2</sub>S wastewater environments
- Suitable for use on primed steel or direct to concrete/masonry
- Good visibility due to light color
- Glossy and smooth appearance
- Reduced explosion risk and fire hazard
- Suitable for storage of unleaded gasolines
- Good chemical resistance against a wide range of chemicals and solvents
- A clear version is available for application of glass mats repair systems or application of chopped glass fibers
- Excellent resistance to crude oil up to 120°C (250°F)
- Can be applied by heavy-duty, single-feed, airless spray equipment (60:1)
- Meets the requirements of EI 1541 2.2 (coating systems for aviation fuel storage tanks and pipes)
- Meets NSF/ANSI Standard 61 for potable water when applied and used as described on <http://info.nsf.org/>

## COLOR AND GLOSS LEVEL

- Green, cream, clear
- Gloss

## BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (10.8 lb/US gal)
Volume solids	100%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 106.0 g/kg max. 142.0 g/l (approx. 1.2 lb/US gal) EPA Method 24: 73.0 g/ltr (0.6 lb/USgal)
Recommended dry film thickness	300 - 600 µm (12.0 - 24.0 mils) depending on system
Theoretical spreading rate	3.3 m <sup>2</sup> /l for 300 µm (134 ft <sup>2</sup> /US gal for 12.0 mils)
Dry to touch	6 hours
Overcoating Interval	Minimum: 24 hours Maximum: 2 months
Full cure after	5 days



# NOVAGUARD™ 840

## Data for mixed product

<b>Shelf life</b>	Base: at least 24 months when stored cool and dry Hardener: at least 24 months when stored cool and dry
-------------------	--

### Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time

## RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

### Carbon steel

- Steel; blast cleaned to a minimum of SSPC-SP10 or ISO-SA2½, blasting profile 50 – 125 µm (5.0 mils) (2.0 – 5.0 mils)
- Steel with suitable primer (NOVAGUARD 260 or PHENGUARD 930) must be dry and free from any contamination

### Concrete

- Remove grease, oil and other penetrating contaminants according to ASTM D4258
- Abrade the surface per ASTM D4259 to remove all chalk and surface glaze or laitance. Achieve surface profile - ICRI CSP 3 to 5
- NOVAGUARD 840 with PPG 884 Additive or AMERCOAT 114A may be used as a pit filler for certain applications. Check with PPG Technical Service for guidance on chemical resistance
- Maximum recommended moisture transmission rate is 3 lbs / 1,000 ft<sup>2</sup> / 24 hours by moisture transmission test (ASTM F1869, calcium chloride test or by ASTM D4263, plastic sheet test)
- Moisture content should not exceed 4% (ASTM D4944, Calcium Carbide Gas method)

### Substrate temperature and application conditions

- Substrate temperature during application and curing should be above 5°C (41°F)
- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point

## INSTRUCTIONS FOR USE

### Mixing ratio by volume: base to hardener 80:20 (4:1)

- The temperature of the mixed base and hardener should preferably be at least 20°C (68°F)
- At lower temperature, the viscosity will be too high for spray application
- No thinner should be added
- For recommended application instructions, see working procedure

### Induction time

None



# NOVAGUARD™ 840

## **Pot life**

1 hour at 20°C (68°F)

Note: See ADDITIONAL DATA – Pot life

## **Airless spray**

- Use heavy-duty, single-feed, airless spray equipment, preferably 60:1 pump ratio and suitable high-pressure hoses/in-line heating or insulated hoses may be necessary to avoid cooling down of paint in hoses at low air temperature
- Length of hoses should be as short as possible

## **Recommended thinner**

No thinner should be added

## **Nozzle orifice**

Approx. 0.53 mm (0.021 in)

## **Nozzle pressure**

At 20°C (68°F) paint temperature min. 28.0 MPa (approx. 280 bar; 4061 p.s.i.). At 30°C (86°F) min. 22.0 MPa (approx. 220 bar; 3191 p.s.i.)

## **Brush/roller**

- Brush: for stripe coating and spot repair only

## **Recommended thinner**

No thinner should be added

## **Cleaning solvent**

THINNER 90-53 or THINNER 90-83

### Notes:

- Paint inside the spraying equipment must be removed before the pot life has been expired
- All application equipment must be cleaned immediately after use

## **ADDITIONAL DATA**

<b>Spreading rate and film thickness</b>	
<b>DFT</b>	<b>Theoretical spreading rate</b>
300 µm (12.0 mils)	3.3 m <sup>2</sup> /l (134 ft <sup>2</sup> /US gal)
600 µm (24.0 mils)	1.7 m <sup>2</sup> /l (67 ft <sup>2</sup> /US gal)

Note: Maximum DFT when brushing: 150 µm (6.0 mils)

# NOVAGUARD™ 840

## Measuring wet film thickness

- A difference is often obtained between the measured apparent WFT and the real applied WFT. This is due to the thixotropy and the surface tension of the paint, which retards the release of air, trapped in the paint film for some time
- Recommendation is to apply a WFT, which is equal to the specified DFT plus 60 µm (2.4 mils)

## Measuring dry film thickness

- Because of low initial hardness the DFT cannot be measured within some days, due to the penetration of the measuring device into the soft paint film
- The DFT should be measured using a calibration foil of known thickness placed in between the coating and the measuring device

Overcoating interval for DFT up to 300 µm (12.0 mils)					
Overcoating with...	Interval	5°C (41°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)
itself	Minimum	3.5 days	36 hours	24 hours	16 hours
	Maximum	3 months	3 months	2 months	1 month

Note: Surface should be dry and free from any contamination

Curing time for DFT up to 300 µm (12.0 mils)			
Substrate temperature	Dry to handle	Minimum cure time for purely aliphatic petroleum product (see note)	Minimum cure time for all other chemicals
5°C (41°F)	60 hours	10 days	15 days
10°C (50°F)	30 hours	5 days	7 days
20°C (68°F)	16 hours	60 hours	5 days
30°C (86°F)	10 hours	36 hours	3 days
40°C (104°F)	6 hours	18 hours	48 hours

### Notes:

- Gasoline or gasoline/alcohol blends are not included in purely aliphatic petroleum products, please contact your PPG representative for further details
- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)

Pot life (at application viscosity)	
Mixed product temperature	Pot life
10°C (50°F)	2 hours
20°C (68°F)	1 hour
30°C (86°F)	45 minutes

Note: Due to exothermic reaction, temperature during and after mixing may increase



# NOVAGUARD™ 840

## Product Qualifications

- Qualified for ANSI/NSF Standard 61 (potable water). For NSF application instructions, please visit the following website: <http://www.nsf.org/certified-products-systems/>

## SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- Ventilation should be provided in confined spaces to maintain good visibility
- If workers are exposed to concentrations above the exposure limit, they must use appropriate personal protective equipment (PPE).

## WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

## REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

## WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

# NOVAGUARD™ 840

## LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at [www.ppgpmc.com](http://www.ppgpmc.com). The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

