



# New Guard Coatings Group

- A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

**RUST-OLEUM®**  
— INDUSTRIAL —



**PEGAKOTE®**

## Very durable water-based epoxy



- Exceptionally abrasion resistant
- Smooth satin gloss finish in almost any colour
- Easy to apply and clean
- Resistant to oils and solvents
- Water-based, very low odour

**KNOW-HOW TO PROTECT™**

**WWW.RUST-OLEUM.EU**

# PEGAKOTE®

## DESCRIPTION

Two-pack, satin gloss epoxy floor paint for garages, warehouses, showrooms, corridors, indoor car parks, workshops etc.

## RECOMMENDED USE

For garages, warehouses, showrooms, corridors, indoor car parks, workshops, etc. Only for indoor works, as well for floors as for walls.

Very abrasion resistant: Taber Abrasion weight loss after 1000 cycles: ± 60 mg (CS10, load: 1000 g)

## TECHNICAL DATA

Density:	1,45
Gloss Level:	Satin
Solids content in volume:	48 - 50 %
Solids Content in weight:	64 - 66 %
Mixing Ratio:	Base : Activator = 6.2 : 1 (Weight)

## DRYING TIMES AT 20°C/RH 50%

Touch dry:	9 hours
Dry to handle:	12 hours
Dry to recoat:	24 hours at 20°C, 48 hours at 8-10 °C
Fully cured:	7 days
Pot Life:	2 hours

## RECOMMENDED WET FILM THICKNESS

200 µm

## RECOMMENDED DRY FILM THICKNESS

100 µm

## THEORETICAL CONSUMPTION

300 g/m<sup>2</sup> for roller & airless application.

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

The substrate should be dry and clean, free from ascending humidity and sufficiently coherent (tensile strength min. 6 kg/cm<sup>2</sup>). Pegakote can be applied directly on most mineral substrates (f.i. old concrete, tiles, glass etc.). Curing compounds in case of poly-concrete have to be removed by means of sand or grit blasting. On new concrete or non-porous concrete, remove cement grout by sand or grit blasting, treatment with diluted hydrochloric acid at a ratio of 3 l hydrochloric acid to 10 l water or with Surfa-Etch 108. For these two last solutions, there is obligation to rinse abundantly and to allow drying through of the surfaces. Porous substrates shall be impregnated with Pegakote diluted with 10 to 20% volume water. Pegakote may not be applied on an elastic paint coat or a moving substrate.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use. Stir the activator thoroughly using an electrical mixer at low speed. Add progressively under stirring to the base. Stir the mixture thoroughly until an even colour and consistency are obtained during minimum 3 minutes. Temperature of the mixed materials should be at least 10°C.

## APPLICATION CONDITIONS

Minimum 8°C and maximum 80% R.H.

## APPLICATION & THINNING: BRUSH

If necessary, dilute with water.

## APPLICATION & THINNING: ROLLER

Dilute 1st coat with maximum 10% volume water.

Apply 2nd coat undiluted.

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 015 - 017 / Pressure: 220 bars.

1st coat: dilute with 5 - 10% volume water.

2nd coat: dilute with max. 5% volume water.

## CLEANING OF EQUIPMENT / SPILLS

Water

## REMARKS

1. In order to become a solid gloss finish, please respect the consumption quantities of the second layer, this means that a tin of 4 kg has to be applied on a surface of 10–13m<sup>2</sup>.
2. Always provide good air ventilation; so even when it rains, windows and doors have to be opened wherever possible.
3. The 2 components must be mixed under mechanical agitation.
4. For use on floors submitted to heavy abrasion, standard and medium colours are recommended. In case of deep and/or bright tones (red, yellow, orange, green, blue etc), it is advised to apply a clear topcoat.

## SAFETY DATA

VOC level:	0 g/l
VOC ready mix:	10 g/l
VOC category:	A/j
VOC limit:	140 g/l
Grenelle:	A+
Flashpoint:	Not flammable
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 06/12/2018

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
info@rust-oleum.eu

**Rust-Oleum UK Ltd.**  
PO Box 261  
Chester-le-Street  
DH3 9EH United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
info@rust-oleum.eu

**Rust-Oleum France S.A.S.**  
11, rue Jules Verne - B.P. 60039  
95322 St-Leu-La-Forêt Cedex  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
info@rust-oleum.eu

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
info@rust-oleum.eu