



New Guard Coatings Group

☐ A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

NATCEM® TANK

Product Data Sheet



Description

NATCEM® TANK is an environmentally friendly, waterproof mortar with rapid strength gain, suitable for installation from **a minimum thickness of 10mm**. The product consists of a blend of Natural Cement binder, retarder and specially selected graded aggregates all passing a 2mm sieve.

NATCEM® TANK is suitable for the following Applications:

- Waterproof Renders
- Damp Proofing
- Wastewater Environments
- Swimming Pools
- Basements & Cellars
- Tanking
- Vaults
- Tanks

Properties

- Only requires the addition of water
- Waterproof
- Sulphate resistant
- Resistant to chloride penetration
- High chemical resistance
- Sets Underwater
- Can be used in freezing temperatures
- Environmentally friendly & low carbon footprint
- Contains no chemical additives
- Extended setting time for longer workability
- Fast cure, can be over-coated one hour after set

Yield & Coverage

Generally, 1 x 25kg bag of NATCEM® TANK mixed with 3.6 litres of water will produce **12.5 litres** of finished mortar. Each 25kg bag of NATCEM® TANK when mixed will cover approximately **1m²** at 10mm depth.

Setting Time & Strength Gain

Start Set End Set	at 20° at 20°
	Compressive Strength (Mpa)
1 Hour	5
3 Hours	11
24 Hours	17
7 Days	19
28 Days	26
Strength continues to develop thereafter.	

Setting Times

NATCEM® TANK is designed to **commence setting at 55 minutes and finish setting at 60 minutes** at 20°C. In winter, NATCEM® TANK can be used down to 0°C. The set will be slower but can be accelerated by using warm water. In hot temperatures, the set will be faster and can be slowed by using cold water or NATCEM® SETTING RETARDER (see separate product data sheet).

NATCEM® TANK



Method of use

Preparation

Do not use on frozen or overheated substrates (0°–30°). Prepare the surface in advance, ensuring it is well roughened to provide an adequate key. Any adhesion-reducing substances such as oil, paint, bitumen, grease or laitance must be removed by suitable means. On glazed brickwork, the joints should be raked out and the surface bush hammered to form a key. The surface to which the NATCEM® TANK is applied should be clean, free from dust and thoroughly dampened. Where necessary, steel or aluminium mesh can be used.

Mixing

Each bag of NATCEM® TANK should be mixed with between **3.6 and 4 litres of water**. For optimum results, mix using conventional mixing machines. Always place the water in the mixer or mixing container and add the powder. Gradually add the NATCEM® TANK to **3.6 litres** of clean water per bag whilst continuously mixing the material. If one bag or less is to be used, the NATCEM® TANK can be mixed with a Rose Bud type paddle attached to an electric drill (900 rpm, 1000w). Mix vigorously for at least 2 minutes after adding all the mixture to the water.

NATCEM® TANK is designed to give a fluid mix, but this only develops after sufficient mixing. The mix will appear dry at first. Continue mixing until fluidity develops. If greater fluidity is required, more water up to a total of **4 litres** may be used. Exceeding this ratio will lead to lower strength, longer setting time and the risk of surface cracking appearing.

Scan to see Installation Video:



www.naturalcement.co.uk



Priming

There is no need to prime any exposed reinforcement but if priming is preferred, a conventional system may be used.

Placing

After mixing, apply the material as quickly as possible using traditional tools. **A 10mm minimum thickness** of the material is always necessary. Do not apply additional water to the surface during finishing, as this may cause surface cracking. Once the setting has started, **DO NOT** attempt to remix or to smooth the surface. This will cause the mechanical properties, in particular strength and adhesion, to be lost.

Precautions & Storage

We strongly recommend the use of GLOVES, GOGGLES and MASKS. Full details are provided in the Safety Data Sheet. Clean all tools with water immediately after use.

NATCEM® TANK is packaged in a polythene inner bag with a resealable tie within a stitch-sealed woven polypropylene outer bag that should be stored in dry conditions and will last for at least twelve months.

Coating

When applying a finishing plaster to the surface of NATCEM® TANK, we recommend using Thistle Board Finish Plaster or Lime Plaster. **We DO NOT recommend using Multi-Finish Plaster.**



01226 381133



enquiries@naturalcement.co.uk



10-11 Fountain Parade, Mapplewell
Barnsley, South Yorkshire
S75 6FW

Ver. 200125