



New Guard Coatings Group

- A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

NOVAGUARD™ 810

DESCRIPTION

Two-component, single coat, solvent-free, amine rapid-cured novolac phenolic epoxy coating

PRINCIPAL CHARACTERISTICS

- Rapid cure and return-to-service
- Cures at temperatures down to -7°C (20°F)
- Excellent resistance to crude oil up to 90°C (194°F)
- Suitable for storage of unleaded gasolines blended up to 100% ethanol (E5 up to E100)
- Good chemical resistance against a wide range of chemicals and solvents
- Smooth finish and light color for easy cleaning and inspection
- Dry heat resistance 120°C (250°F)
- Hydrocarbon immersion after only 1 day at 20°C (68°F)
- Meets the requirements of EI 1541, section 2.2

COLOR AND GLOSS LEVEL

- Cream (Light Gray on request)
- Semi-gloss

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	Two
Mass density	1.3 kg/l (11.0 lb/US gal)
Volume solids	98 ± 2%
VOC (Supplied)	EPA Method 24: 97.0 g/ltr (0.8 lb/USgal) max. 190.0 g/l (approx. 1.6 lb/US gal)
Recommended dry film thickness	400 - 1000 µm (16.0 - 40.0 mils) depending on system
Theoretical spreading rate	2.5 m ² /l for 400 µm (98 ft ² /US gal for 16.0 mils)
Dry to touch	4 hours
Full cure after	48 hours
Shelf life	Base: at least 12 months when stored cool and dry Hardener: at least 12 months when stored cool and dry

Notes:

- See ADDITIONAL DATA – Spreading rate and film thickness
- See ADDITIONAL DATA – Overcoating intervals
- See ADDITIONAL DATA – Curing time



NOVAGUARD™ 810

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Substrate conditions

- Steel; blast cleaned to a minimum of SSPC-SP10 or ISO-SA2½, blasting profile 50 – 125 µm (2.0 – 5.0 mils)
-

Substrate temperature and application conditions

- Substrate temperature during application and curing down to -7°C (20°F) is acceptable; provided the substrate is free from ice and dry
 - Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
-

INSTRUCTIONS FOR USE

Mixing ratio by volume: base to hardener 80:20 (4:1)

- The temperature of the mixed base and hardener should preferably be at least 40°C (104°F)
 - At lower temperature, the viscosity will be too high for spray application
 - No thinner should be added
 - For recommended application instructions, see working procedure
-

Induction time

None

Airless spray

- Use heated, airless spray, plural-component equipment
- In-line heating or insulated hoses may be necessary to avoid cooling down of paint in hoses at low air temperature
- Length of hoses should be as short as possible

Recommended thinner

No thinner should be added

Nozzle orifice

Approx. 0.58 mm (0.023 in)

Nozzle pressure

28.0 MPa (approx. 280 bar; 4061 p.s.i.)

Notes:

- For optimal flow and leveling on horizontal areas having a substrate temperature below 20°C (68°F), the paint temperature (spray fan) should be kept typically below 30°C (86°F). The distance between the spray gun and the substrate should be low, for example less than 50 cm (20 inch)
 - For optimal flow and sag resistance on vertical areas having a substrate temperature above 20°C (68°F), the paint temperature (spray fan) should be kept typically above 30°C (86°F)
-

NOVAGUARD™ 810

Cleaning solvent

THINNER 90-53 or THINNER 90-83

Note: All application equipment must be cleaned immediately after use. Paint inside the spraying equipment must be removed before the pot life has been expired.

ADDITIONAL DATA

Spreading rate and film thickness	
DFT	Theoretical spreading rate
400 µm (16.0 mils)	2.5 m ² /l (98 ft ² /US gal)
600 µm (24.0 mils)	1.6 m ² /l (65 ft ² /US gal)

Measuring wet film thickness

- A difference is often obtained between the measured apparent WFT and the real applied WFT. This is due to the thixotropy and the surface tension of the paint, which retards the release of air, trapped in the paint film for some time
- Recommendation is to apply a WFT, which is equal to the specified DFT plus 60 µm (2.4 mils)

Measuring dry film thickness

- The DFT should be measured using a calibration foil of known thickness placed in between the coating and the measuring device

Minimum Overcoating interval for spot repairs							
Overcoating with...	Interval	-5°C (23°F)	0°C (32°F)	10°C (50°F)	20°C (68°F)	30°C (86°F)	40°C (104°F)
itself	Minimum	48 hours	24 hours	12 hours	6 hours	4 hours	3 hours
	Maximum	See below note(s)	See below note(s)	See below note(s)	See below note(s)	See below note(s)	See below note(s)

Notes:

- For spot repairs, surface needs to be prepared by abrading until a matt finish is obtained. Larger areas require sweep blasting.
- Due to the short pot life of NovaGuard 810, it is recommended to do stripe or repair coating with NovaGuard 890
- Surface should be dry and free from any contamination and ice

NOVAGUARD™ 810

Curing time for DFT up to 1000 µm (40.0 mils)		
Substrate temperature	Dry to handle	Full cure
-7°C (20°F)	7 days	28 days
0°C (32°F)	3 days	9 days
5°C (41°F)	36 hours	5 days
10°C (50°F)	20 hours	3 days
20°C (68°F)	9 hours	48 hours
30°C (86°F)	7 hours	24 hours
40°C (104°F)	4 hours	12 hours

Notes:

- Adequate ventilation must be maintained during application and curing (please refer to INFORMATION SHEETS 1433 and 1434)
- For storage and transport of drinking water the recommended working procedure should be followed
- Holiday test can be done after dry to handle time

Pot life (at application viscosity)	
Mixed product temperature	Pot life
20°C (68°F)	15 minutes
30°C (86°F)	10 minutes

Note: It is recommended to use plural airless equipment due to the short pot life

Product Qualifications

- ANSI / NSF Standard 61 for drinking water (for tank and pipe). For more information, please visit NSF website at: www.nsf.org/certified-products-systems/
- Compliant with EI 1541, Performance requirements for protective coating systems used in aviation fuel storage tanks and piping

SAFETY PRECAUTIONS

- For paint and recommended thinners see INFORMATION SHEETS 1430, 1431 and relevant Material Safety Data Sheets
- Although this is a solvent-free paint, care should be taken to avoid inhalation of spray mist, as well as contact between the wet paint and exposed skin or eyes
- Ventilation should be provided in confined spaces to maintain good visibility
- If workers are exposed to concentrations above the exposure limit, they must use appropriate personal protective equipment (PPE).

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.



NOVAGUARD™ 810

REFERENCES

• CONVERSION TABLES	INFORMATION SHEET	1410
• EXPLANATION TO PRODUCT DATA SHEETS	INFORMATION SHEET	1411
• SAFETY INDICATIONS	INFORMATION SHEET	1430
• SAFETY IN CONFINED SPACES AND HEALTH SAFETY, EXPLOSION HAZARD – TOXIC HAZARD	INFORMATION SHEET	1431
• SAFE WORKING IN CONFINED SPACES	INFORMATION SHEET	1433
• DIRECTIVES FOR VENTILATION PRACTICE	INFORMATION SHEET	1434
• CLEANING OF STEEL AND REMOVAL OF RUST	INFORMATION SHEET	1490
• SPECIFICATION FOR MINERAL ABRASIVES	INFORMATION SHEET	1491
• RELATIVE HUMIDITY – SUBSTRATE TEMPERATURE – AIR TEMPERATURE	INFORMATION SHEET	1650

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

