



# New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

[www.newguardcoatings.com](http://www.newguardcoatings.com)

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

# PLANITOP HPC FLOOR 46

Ultra high-performance high ductility free-flowing micro-concrete reinforced with metal fibres



## WHERE TO USE

Repairing and strengthening horizontal structures where high-performance, free-flowing mortar is required to integrate thick layers or fill complex areas.

### Some application examples

- Seismic upgrading of elements exposed to high stresses where high ductility is required.
- Structural strengthening by casting a thin support layer on the outer face of reinforced concrete, brick-cement, timber and brick-steel beams floorings.
- Repairs to concrete floors (industrial floors, roads, airport road surfaces).
- Reconstructing and levelling off the upper parts of pavements and bearing elements of piles for motorway viaducts.
- Reintegrating floor beams after removing damaged areas by scarifying.

## TECHNICAL CHARACTERISTICS

**Planitop HPC Floor 46** is a ready-mixed powdered micro-concrete made from high-strength cement, selected aggregates, special admixtures and stiff steel fibres according to a formula developed in the MAPEI Research & Development laboratories.

When **Planitop HPC Floor 46** is mixed with water it forms a fluid micro-concrete suitable for casting into formwork without segregating in layers from 2 to 8 cm thick, and without the need for electro-welded reinforcing mesh.

To allow the product's expansive properties to develop fully and correctly, **Planitop HPC Floor 46** must be mixed with water and cured in a damp environment. To allow expansion in the open air, **Planitop HPC Floor 46** may also be admixed with 0.25% of **Mapecure SRA**, a special admixture which has the capacity to reduce plastic and hydraulic shrinkage.

**Mapecure SRA** carries out an extremely important role and guarantees better curing of the micro-concrete. When mixed with **Planitop HPC Floor 46** it may be considered a technologically advanced system, in that the admixture has the capacity to stop the water evaporating too quickly from the micro-concrete and encourages the development of hydration reactions.

**Mapecure SRA** acts basically as an internal curing agent and, thanks to its interaction with some of the main components in the cement, it reduces final shrinkage by 20% to 50% compared with the same product without the admixture, which means there is also a lower risk of cracking.

The use of **Mapecure SRA** may reduce mechanical performance characteristics slightly by 5-6%.


The product may also be used without adding **Mapecure SRA** when climatic conditions allow a favourable curing cycle to be carried out.

Once hardened, **Planitop HPC Floor 46** has the following characteristics:

- very high flexural and compressive strength;
- high ductility;
- high resistance to cyclical loads;
- impermeable to water;
- excellent adhesion to old concrete, if dampened with water before application, and to rebar, especially if treated beforehand with **Mapefer** or **Mapefer 1K**;
- high resistance to wear from abrasion or impact loads.

**Planitop HPC Floor 46** complies with the principles defined in EN 1504-9 ("*Products and systems for protecting and repairing concrete structures: definitions, requirements, quality control and conformity assessment. General principles for the use and application of systems*"), and the minimum requirements of EN 1504-3 ("*structural and non-structural repairs*") for R4-class structural mortars.

**Planitop HPC Floor 46** is covered by the Certificate of Technical Assessment (CVT) n° 264/2020 released by 2<sup>^</sup> Div. II of STC - CSLP.



Typical residual flexural strength behaviour in compliance with EN 14651

## RECOMMENDATIONS

- Do not use **Planitop HPC Floor 46** on smooth concrete substrates.
- Do not use **Planitop HPC Floor 46** for anchoring elements accurately in place (use **Mapefill** or **Mapefill R**).
- Do not apply **Planitop HPC Floor 46** by spray or with a trowel (use **Planitop HPC Tixo** applied by trowel.)
- Do not add cement or admixtures to **Planitop HPC Floor 46**.
- Do not add water once the mix has started to set.
- Do not use **Planitop HPC Floor 46** if the bag is damaged or if it has been opened previously.

## APPLICATION PROCEDURE

### Preparation of the substrate

- Remove all deteriorated concrete and any concrete that is loose or detached down to the level of the substrate. The substrate must be solid and strong with a surface roughness of at least 5 mm. Any areas previously repaired and which are not perfectly bonded must be removed.
- Remove all dust, rust, cement laitance, grease, oil and old paint from the concrete and rebar by sandblasting.
- If the substrate needs to be consolidated, apply a coat of **Primer 3296** diluted 1:1 with water at least 4 hours before applying **Planitop HPC Floor 46**.
- Saturate the substrate with water. Before casting the product, wait until excess surface water has evaporated off. Use compressed air to accelerate this process if required.

### Preparation of the micro-concrete

Pour **Planitop HPC Floor 46** in the mixer and add 2.5 litres of water per each bag of product used. Mixing time of the product depends on the efficiency of the employed mixer. For example, with a forced-action mixer, mixing requires approximately 5 minutes. If a traditional cement mixer is used, mixing requires approximately 12 minutes. Stir until fibres are completely dispersed and a homogeneous, fluid and lump-free mix is obtained. Mixing water may vary slightly (2.4 -2.6 litres) to cope with different types of mixers used and weather conditions on site. It is recommended to apply the product within 30 minutes of mixing.

### Application of the micro-concrete on floor slabs

Pour **Planitop HPC Floor 46** onto the surface and, if necessary, help the mortar spread over the surface with a rake.

### Application of the micro-concrete into formwork

Pour **Planitop HPC Floor 46** into the formwork in a continuous flow from one side only, and make sure all the air is expelled. The formwork must not absorb any of the water from **Planitop HPC Floor 46**, so we recommend treating the formwork beforehand with a form-release agent (such as **DMA 1000**). Make sure all the elements to be reinforced are completely filled. To help the mortar flow into the more difficult areas, use wooden rods or round bars or vibrate slightly.



Bending test in compliance with EN 14651

## PRECAUTIONS TO BE TAKEN DURING AND AFTER APPLICATION

- Only use bags of **Planitop HPC Floor 46** which have been stored on their original, covered pallets.
- In hot weather, store the product in a cool area and use cold water to prepare the mix.
- In cold weather, store the product in a closed area at a temperature of +20°C and protect from frost. Use lukewarm water to prepare the micro-concrete.
- We recommend curing **Planitop HPC Floor 46** carefully immediately after pouring to prevent the mixing water evaporating off too quickly, especially in hot or windy weather, otherwise surface cracks may appear. Protect **Planitop HPC Floor 46** at all times by spraying the surface with a water mist while pouring operations are being carried out. Then immediately cover it with waterproof sheets and keep covered for at least 5 days.

## CLEANING

Micro-concrete may be cleaned from tools before it hardens using water. Once hardened, cleaning is much more difficult and it must be removed mechanically.

## CONSUMPTION

Approx. 22 kg/m<sup>2</sup> per cm of thickness.

## PACKAGING

**Planitop HPC Floor 46** is supplied in 25 kg bags or 1,000 kg big-bags.

## STORAGE

**Planitop HPC Floor 46** may be stored for 12 months in its original packaging in a dry, covered area.

## SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Instructions for the safe use of our products can be found on the latest version of the SDS, available from our website [www.mapei.com](http://www.mapei.com).

PRODUCT FOR PROFESSIONAL USE.

TECHNICAL DATA (typical values)	
PRODUCT IDENTITY	
Class according to EN 1504-3:	R4
Type:	CC

<b>CEMENTITIOUS MATRIX</b>	
Consistency:	powder
Colour:	grey
Bulk density (kg/m <sup>3</sup> ):	1,400
Maximum size of aggregate (mm):	6.0
Dry solids content (%):	100
Ion chloride content – minimum requirement ≤ 0.05% - according to EN 1015-17 (%)	≤ 0.05
<b>FIBRES</b>	
Shape:	hooked
Material:	steel
Density of material according to EN 14889-1 (g/cm <sup>3</sup> ):	7.85
Length according to EN 14889-1 (mm):	30
Diameter according to EN 14889-1 (mm):	0.38
Tensile strength according to EN 14889-1 (MPa):	3070
Modulus of elasticity according to EN 14889-1 (GPa):	200
Elongation at failure according to EN 14889-1 (%):	min. 0.70
<b>APPLICATION DATA (at +20°C - 50% R.H.)</b>	
Colour of mix:	grey
Mixing ratio:	100 parts of <b>Planitop HPC</b> with 9.5-10.5 parts of water (2.4-2.6 l water per 25 kg bag)
Consistency class according to EN 12350-8:	SF3
Viscosity class- t <sub>500</sub>	VS2
Density according to EN 12390-7 (kg/m <sup>3</sup> ):	2,460
pH of mix:	> 12.5
Application temperature range:	+5°C to +35°C
Pot life of mix:	approx. 45 minutes (at +20°C)

Set to light foot traffic:	24 h (at +20°C)		
Set to heavy foot traffic:	72 h (at +20°C)		
<b>FINAL PERFORMANCE (10% mixing water - Mixing*)</b>			
Performance characteristic	Test method	Requirements according to EN 1504-3 for R4 class mortars	Performance of product
Compressive strength (MPa):	EN 12190	≥ 45 (after 28 days)	125 (after 28 days)
Compressive modulus of elasticity (GPa):	EN 13412	≥ 20 (after 28 days)	38 (after 28 days)
Shear strength and slip resistance ( $\tau$ -bond) concrete substrate with roughened surface (MPa):	Experimental method (**)	none	≥ 3.0
Adhesion to concrete (MC 0.40 substrate type - w/c ratio = 0.40) according to EN 1766 (MPa):	EN 1542	≥ 2 (after 28 days)	≥ 3 (after 28 days)
Accelerated carbonatation resistance:	EN 13295	Depth of carbonatation ≤ than reference concrete (MC 0.45 type w/c ratio = 0.45) according to UNI 1766	Test passed
Capillary absorption ( $\text{kg/m}^2 \cdot \text{h}^{0.5}$ ):	EN 13057	≤ 0.5	< 0.5
Impermeability to water - penetration depth (mm):	EN 12390-8	none	< 2
Thermal compatibility measured as bond strength according to EN 1542 (MPa): – freeze-thaw cycles with de-icing salts:	EN 13687/1	≥ 2 (after 50 cycles)	> 2
Resistance to freeze-thaw cycles in presence of salts - flaking ( $\text{g/m}^2$ ):	EN 12390-9	none	< 100 (after 56 cycles)
Slip resistance of steel reinforcing bars - movement under a load of 75 kN (mm):	EN 1881	none	< 0.6
Residual flexural strength (MPa): – CMOD 1 = 500 $\mu\text{m}$ : – CMOD 2 = 1,500 $\mu\text{m}$ : – CMOD 3 = 2,500 $\mu\text{m}$ : – CMOD 4 = 3,500 $\mu\text{m}$ :	EN 14651	none	$f_{R1}$ 11.9 $f_{R2}$ 12.6 $f_{R3}$ 12.0 $f_{R4}$ 10.2
Reaction to fire:	EN 13501-1	Euroclass	A1, A1 <sub>FL</sub>

(\*) Mixing: see paragraph "Preparation of the mortar".

For this type of product, the preparation of test samples (cubes and beams) requires compaction with a concrete vibrator (in compliance with § 3.3 EN 12390-2).

(\*\*) Experimental method. Test report available on request (contact Technical Services).

<b>MECHANICAL PROPERTIES AND DURABILITY according to CVT n° 264/2020 (mixing water 12%)</b>		
PROPERTIES	Test method / norm reference	Performance of product

Compressive strength Class:	NTC 2018 Tab. 4.1.1	C 80/95
Compressive modulus of elasticity (GPa):	NTC 2018 § 11.2.10.3	43.2 (charted value)
Toughness class:	EN 14651	8.0 c
Tensile strength at limit of proportionality: – average value $f_{ct,L,m}$ (MPa): – typical value $f_{ct,L,k}$ (MPa):	EN 14651	7.5 6.7
Exposure class:	EN 206-1	X0 XC1, XC2, XC3, XC4 XD1, XD2, XD3 XS1, XS2, XS3 XF1, XF2, XF3, XF4 (***) XA1
Resistance to freeze-thaw cycles:	FRC Guidelines (January 2019) § 3.4.1	Test passed

(\*\*\*) **Planitop HPC Floor 46** has been tested according to EN 12390-9 by comparing it with reference concrete with a composition specified for class XF4 according to EN 206-1 standards.

## WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website [www.mapei.com](http://www.mapei.com)

## LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website [www.mapei.com](http://www.mapei.com).

**ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.**

1149-8-2020-gb

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

