



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

Quality Paints since 1845
MATHYS[®]



PARACEM[®] SEMI-GLOSS

Waterborne semi-gloss acrylic paint



- For indoor and outdoor works
- Very decorative semi-gloss aspect
- Easy to clean and to maintain
- High filling and hiding power
- Excellent flow out

PARACEM® SEMI-GLOSS

DESCRIPTION

Waterborne semi-gloss acrylic paint for inner and outer walls.

RECOMMENDED USE

Durable painting of old and new masonry, cement, concrete or plaster.

RECOMMENDED SYSTEM

Substrate/Condition	Primer/Preparation	Finish
Porous substrates	Pegafix or Parafix/Paracem (50/50)	2 coats Paracem SG
Very smooth/non porous	Noxyde diluted with 25% water or Pegalink	2 coats Paracem SG
Sound old paints (no chalking)	-	2 coats Paracem SG
Sound old paints (chalking)	Fixonal or Pegafix	2 coats Paracem SG
Cracks and holes	Fill with Elastofill or Mur-Filler	-
Uneven substrate	Fill with Pegaflex. Sand, remove dust and prime with	2 coats Paracem SG

TECHNICAL DATA

Density (g/cm ³):	1,28 - 1,32
Gloss Level:	Satin
Gloss level at 60°:	Semi-Gloss: 65%
Solids Content in weight:	50 - 53 %
Solids content in volume:	35 - 38 %

DRY TIMES BY 20° C/RV 50%

Touch dry:	40 minutes
Dry to handle:	2 hours
Dry to recoat:	4 hours
Fully cured:	1 day

RECOMMENDED WET FILM THICKNESS

125 µm

RECOMMENDED DRY FILM THICKNESS

45 µm

THEORETICAL CONSUMPTION

8 - 10 m²/l

PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

The substrate must be sufficiently dry (max. 4% moisture content) and stable. Clean walls

thoroughly with steel brush or high pressure water cleaning. In case of fungal growth: treat the walls first with an adequate moss-preventing product.

DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION CONDITIONS

> 5°C, < 80% R.H.

APPLICATION & THINNING: BRUSH

Apply in 2 coats by preference. Use a synthetic brush for application of waterbased products.

APPLICATION & THINNING: ROLLER

Apply in 2 coats by preference. Use short nap roller (texture polyamide roller 14 mm).

APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 018 / Pressure: 180 bars. 1 coat is sufficient in most cases.

APPLICATION & THINNING: AIR-ATOMISED SPRAY

Not recommended.

CLEANING OF EQUIPMENT / SPILLS

Water.

SAFETY DATA

VOC level:	15 g/l
VOC ready mix:	15 g/l
VOC category:	A/c
VOC limit:	40 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

SHELF LIFE

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 20/08/2020

Available colours & pack sizes: Please refer to the respective product page on www.rust-oleum.eu for an overview of actual available colours and pack sizes.

Disclaimer: The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from www.rust-oleum.eu or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu