



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

SIGMA EP 112 MIOCOAT

4 pages

August 2012
Revision of October 2007

Description

two component high solids micaceous iron oxide pigmented polyamine cured recoatable epoxy coating

PRINCIPAL CHARACTERISTICS

- general purpose epoxy build coat in protective coating systems for steel and concrete structures exposed to atmospheric land or marine conditions
- good adhesion characteristics for subsequent coats
- free from lead and chromate containing pigments
- excellent durability
- easy application, both by airless spray and brush
- VOC compliant
- resistant to temperatures up to 200°C in dry atmospheric exposure conditions
- approved Network Rail RT 98 item 7.2.1
- registered as Highway Agency item 112

COLOURS AND GLOSS

dark grey, light grey – eggshell

BASIC DATA AT 20 °C

(1 g/cm³ = 8.35 lb/US gal; 1 m²/l = 40.7 ft²/US gal)
(data for mixed product)

Mass density	1.8 g/cm ³
Volume solids	70% ± 2%
VOC (UK PG 6/23(92) appendix 3)	max. 245 g/l (approx. 2.0 lb/gal) (UK PG 6/23(92) Appendix 3)
Recommended dry film thickness	75 - 150 µm depending on system
Theoretical spreading rate	7.0 m ² /l for 100 µm
Touch dry after	2 hours at 20 °C
Overcoating interval	min. 8 hours * max. 6 months
Full cure after	7 days * at 20 °C (data for components)
Shelf life (cool and dry place)	at least 24 months * see additional data

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

- steel; blast cleaned to ISO-Sa2½
- during application and curing a substrate temperature down to +5°C , overcoating times are affected as stated in the tables
- substrate temperature at least 3°C above dew point
- maximum relative humidity during application and curing is 85%
- previous suitable coat; dry and free from any contamination

SIGMA EP 112 MIOCOAT

August 2012

mixing ratio by volume: base to hardener 80 : 20

INSTRUCTIONS FOR USE

- the temperature of the mixed base and hardener should preferably be above 15°C, otherwise extra solvent may be required to obtain application viscosity
- too much solvent results in reduced sag resistance and slower cure
- thinner should be added after mixing the components

Pot life

6 hours at 20 °C

AIR SPRAY

Recommended thinner

Thinner 91-92

Volume of thinner

10 - 15%, depending on required thickness and application conditions

Nozzle orifice

1.5 - 3 mm

Nozzle pressure

0.3 - 0.4 MPa (= approx. 3 - 4 bar; 44 - 58 p.s.i.)

AIRLESS SPRAY

Recommended thinner

Thinner 91-92

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

approx. 0.48 - 0.58 mm (= 0.019 - 0.023 in)

Nozzle pressure

15 MPa (= approx. 150 bar; 2176 p.s.i.)

BRUSH/ROLLER

Recommended thinner

Thinner 91-92

Volume of thinner

0 - 5%

CLEANING SOLVENT

- Thinner 90-53

Film thickness and spreading rate

theoretical spreading rate m ² /l	9.3	7.0	4.7
dft in µm	75	100	150

Overcoating table for Sigma EP 112 Miocoat

substrate temperature	5°C	10°C	20°C	30°C	40°C
minimum interval	36 hours	16 hours	8 hours	6 hours	4 hours
maximum interval	6 months	6 months	6 months	3 months	1 month

- for polyurethane paints the minimum overcoating time should be raised with 100%

SIGMA EP 112 MIOCOAT

August 2012

Curing

Curing table for Sigma EP 112 Miocoat for dft up to 100 µm

substrate temperature	full cure	dry to handle
5°C	21 days	18 hours
10°C	15 days	8 hours
15°C	10 days	6 hours
20°C	7 days	4 hours
25°C	5 days	4 hours

- adequate ventilation must be maintained during application and curing (please refer to sheets 1433 and 1434)

Worldwide availability

Whilst it is always the aim of Sigma Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

REFERENCES

Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Safe working in confined spaces	see information sheet 1433
Directives for ventilation practice	see information sheet 1434
Cleaning of steel and removal of rust	see information sheet 1490

SAFETY PRECAUTIONS

- for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets
- this is a solvent borne paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

SIGMA EP 112 MIOCOAT

August 2012

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product.

THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG.

Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT.

The information in this data sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk.

PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results.

This data sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this data sheet is current prior to using the product. Current data sheets for all PPG Protective & Marine Coatings products are maintained at www.ppgmc.com.

The English text of this data sheet shall prevail over any translation thereof.

PDS

0709UK