

New Guard Coatings Group

A global reputation to protect.

You have acquired this data sheet from the New Guard Coatings Group.

All information listed is correct at the time of print.



uksales@newguardcoatings.com



+44 1937 586311

Global Head Office: New Guard Coatings Ltd, Sandbeck Way, Wetherby, Leeds, LS22 7DN



DIMETCOTE® 11

DESCRIPTION

One-component, inorganic zinc silicate coating

PRINCIPAL CHARACTERISTICS

- Heavy duty primer that protects with just a single coat
- Good anticorrosive properties
- Dry heat resistance up to 400°C (750°F)

COLOR AND GLOSS LEVEL

- Gray
- Flat

BASIC DATA AT 20°C (68°F)

Data for mixed product	
Number of components	One
Mass density	2.1 kg/l (17.5 lb/US gal)
Volume solids	58 ± 2%
VOC (Supplied)	Directive 1999/13/EC, SED: max. 263.0 g/kg UK PG 6/23(92) Appendix 3: max. 559.0 g/l (approx. 4.7 lb/US gal)
Recommended dry film thickness	65 µm (2.6 mils)
Theoretical spreading rate	8.9 m ² /l for 65 µm (358 ft ² /US gal for 2.6 mils)
Dry to touch	4 minutes
Overcoating Interval	Minimum: 16 hours See overcoating tables
Shelf life	At least 9 months when stored cool and dry

Notes:

- See ADDITIONAL DATA - Overcoating intervals
- See ADDITIONAL DATA - Curing time

RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES

Atmospheric exposure conditions

- Steel; blast cleaned to ISO Sa 2½ or SSPC-SP-10, blasting profile 35 – 65 µm (1.4 – 2.6 mils)
- Previous coat of approved coating must be dry and free from any contamination

Substrate temperature

- Substrate temperature during application and curing should be at least 3°C (5°F) above dew point
- Relative humidity during application should be between 50% and 95%



DIMETCOTE® 11

INSTRUCTIONS FOR USE

- Stir well before use
- The temperature of the paint should preferably be above 15°C (59°F), otherwise extra thinner may be required to obtain application viscosity
- Adding too much thinner results in reduced sag resistance

Air spray

Recommended thinner

THINNER 21-06

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

1.5 - 3.0 mm (approx. 0.060 - 0.110 in)

Nozzle pressure

0.2 - 0.3 MPa (approx. 2 - 3 bar; 29 - 44 p.s.i.)

Airless spray

Recommended thinner

THINNER 21-06

Volume of thinner

5 - 10%, depending on required thickness and application conditions

Nozzle orifice

Approx. 0.43 mm (0.017 in)

Nozzle pressure

10.0 - 15.0 MPa (approx. 100 - 150 bar; 1451 - 2176 p.s.i.)

Brush/roller

Recommended thinner

THINNER 21-06

Volume of thinner

0 - 3%

Cleaning solvent

THINNER 21-06



DIMETCOTE® 11

ADDITIONAL DATA

Overcoating interval for DFT up to 65 µm (2.6 mils)			
Overcoating with...	Interval	10°C (50°F)	20°C (68°F)
itself	Minimum	24 hours	16 hours
	Maximum	3 months	3 months

Notes:

- Zinc rich primers can form zinc salts on the surface; preferably they should not be weathered for long periods before overcoating
- An interval of several months can be allowed under clean interior exposure conditions
- In clean exterior conditions, a maximum interval of 14 days can be tolerated, but in industrial or marine conditions this interval should be reduced to the practical minimum
- Before overcoating visible surface contamination must be removed by high-pressure water cleaning, sweep blasting or mechanical cleaning

Curing time for DFT up to 65 µm (2.6 mils)		
Substrate temperature	Dry to handle	Full cure
10°C (50°F)	10 minutes	30 minutes
20°C (68°F)	7 minutes	20 minutes

Notes:

- Adequate ventilation must be maintained during application and curing
- Drying times are dependent on air and surface temperatures as well as film thickness, ventilation and relative humidity
- Times are proportionally shorter at higher temperature and longer at lower temperatures

SAFETY PRECAUTIONS

- This is a solvent-borne paint and care should be taken to avoid inhalation of spray mist or vapor, as well as contact between the wet paint and exposed skin or eyes

WORLDWIDE AVAILABILITY

It is always the aim of PPG Protective and Marine Coatings to supply the same product on a worldwide basis. However, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances. Under these circumstances an alternative product data sheet is used.

WARRANTY

PPG warrants (i) its title to the product, (ii) that the quality of the product conforms to PPG's specifications for such product in effect at the time of manufacture and (iii) that the product shall be delivered free of the rightful claim of any third person for infringement of any U.S. patent covering the product. THESE ARE THE ONLY WARRANTIES THAT PPG MAKES AND ALL OTHER EXPRESS OR IMPLIED WARRANTIES, UNDER STATUTE OR ARISING OTHERWISE IN LAW, FROM A COURSE OF DEALING OR USAGE OF TRADE, INCLUDING WITHOUT LIMITATION, ANY OTHER WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR USE, ARE DISCLAIMED BY PPG. Any claim under this warranty must be made by Buyer to PPG in writing within five (5) days of Buyer's discovery of the claimed defect, but in no event later than the expiration of the applicable shelf life of the product, or one year from the date of the delivery of the product to the Buyer, whichever is earlier. Buyer's failure to notify PPG of such non-conformance as required herein shall bar Buyer from recovery under this warranty.

DIMETCOTE® 11

LIMITATIONS OF LIABILITY

IN NO EVENT WILL PPG BE LIABLE UNDER ANY THEORY OF RECOVERY (WHETHER BASED ON NEGLIGENCE OF ANY KIND, STRICT LIABILITY OR TORT) FOR ANY INDIRECT, SPECIAL, INCIDENTAL, OR CONSEQUENTIAL DAMAGES IN ANY WAY RELATED TO, ARISING FROM, OR RESULTING FROM ANY USE MADE OF THE PRODUCT. The information in this sheet is intended for guidance only and is based upon laboratory tests that PPG believes to be reliable. PPG may modify the information contained herein at any time as a result of practical experience and continuous product development. All recommendations or suggestions relating to the use of the PPG product, whether in technical documentation, or in response to a specific inquiry, or otherwise, are based on data, which to the best of PPG's knowledge, is reliable. The product and related information is designed for users having the requisite knowledge and industrial skills in the industry and it is the end-user's responsibility to determine the suitability of the product for its own particular use and it shall be deemed that Buyer has done so, as its sole discretion and risk. PPG has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. Therefore, PPG does not accept any liability arising from any loss, injury or damage resulting from such use or the contents of this information (unless there are written agreements stating otherwise). Variations in the application environment, changes in procedures of use, or extrapolation of data may cause unsatisfactory results. This sheet supersedes all previous versions and it is the Buyer's responsibility to ensure that this information is current prior to using the product. Current sheets for all PPG Protective & Marine Coatings Products are maintained at www.ppgpmc.com. The English text of this sheet shall prevail over any translation thereof.

The PPG logo, and all other PPG marks are property of the PPG group of companies. All other third-party marks are property of their respective owners.

