



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

Jotamastic SF

Product description

This is a two component polyamine cured epoxy mastic coating. It is a surface tolerant, solvent free, high build product. Well suited for early immersion. Specially designed for areas where optimum surface preparation is not possible or required. Provides long lasting protection in environments with high corrosivity. Can be used as primer, mid coat, finish coat or as single coat system in atmospheric and immersed environments. Suitable for properly prepared carbon steel and aged coating surfaces.

Typical use

General:

Primarily designed for maintenance and repair.

Marine:

Outside hulls, exterior and interior areas, including water ballast tanks. Suitable for water ballast tanks at newbuilding stage.

Protective:

Recommended for offshore environments, including splash zones, refineries, power plants, bridges, buildings, mining equipment and general structural steel.

Approvals and certificates

Grain, Newcastle Occupational Health

Approved for PSPC for Water Ballast Tanks according to IMO Res. MSC 215(82)

Contributes to satisfying the following credit(s):

- Indoor Environmental Quality (IEQ) under LEED® 2009

When used as part of an approved scheme, this material has the following certification:

- Low Flame Spread in accordance with EU Directive for Marine Equipment. Approved in accordance with parts 5 and 2 of Annex 1 of IMO 2010 FTP Code, or Parts 5 and 2 of Annex 1 of IMO FTPC when in compliance with IMO 2010 FTP Code Ch. 8

Consult your Jotun representative for details.

Additional certificates and approvals may be available on request.

Colours

grey, off-white, red

Product data

Property	Test/Standard	Description
STANDARD GRADE		
Solids by volume	calculated	99 ± 2 %
Gloss level (GU 60 °)	ISO 2813	gloss (70-85)
Flash point	ISO 3679 Method 1	95 °C
Density	calculated	1.5 kg/l
VOC-US/Hong Kong	US EPA method 24 (tested) (CARB(SCM)2007, SCAQMD rule 1113, Hong Kong)	180 g/l
VOC-EU	IED (2010/75/EU) (theoretical)	116 g/l

VOC-Korea	Korea Clean Air Conservation Act (tested) (Max. thinning ratio included)	119 g/l
-----------	---	---------

WINTER GRADE

Solids by volume	calculated	91 ± 2 %
Flash point	ISO 3679 Method 1	56 °C
Density	calculated	1.5 kg/l
VOC-US/Hong Kong	US EPA method 24 (tested) (CARB(SCM)2007, SCAQMD rule 1113, Hong Kong)	220 g/l
VOC-EU	IED (2010/75/EU) (theoretical)	149 g/l
VOC-Korea	Korea Clean Air Conservation Act (tested)	152 g/l

The provided data is typical for factory produced products, subject to slight variation depending on colour.
Gloss description: According to Jotun Performance Coatings' definition.

Film thickness per coat

Typical recommended specification range

STANDARD GRADE

Dry film thickness	150 - 300 µm
Wet film thickness	150 - 300 µm
Theoretical spreading rate	6.1 - 3.1 m ² /l

WINTER GRADE

Dry film thickness	150 - 300 µm
Wet film thickness	165 - 330 µm
Theoretical spreading rate	5.5 - 2.7 m ² /l

Surface preparation

Surface preparation summary table

Substrate	Surface preparation	
	Minimum	Recommended
Carbon steel	St 2 (ISO 8501-1)	Sa 2 (ISO 8501-1)
Shop primed steel	Clean, dry and undamaged shop primer (ISO 12944-4 5.4)	Sa 2 (ISO 8501-1)
Coated surfaces	Clean, dry and undamaged compatible coating	Clean, dry and undamaged compatible coating

Optimum performance, including adhesion, corrosion protection, heat resistance and chemical resistance is achieved with recommended surface preparation.

Application

Application methods

The product can be applied by

Spray:	Use airless spray with high pressure ratio (min. 60:1).
Brush:	Recommended for stripe coating and small areas. Care must be taken to achieve the specified dry film thickness.
Roller:	May be used for small areas. Not recommended for first primer coat. Care must be taken to achieve the specified dry film thickness.

Product mixing ratio (by volume)

STANDARD GRADE

Jotamastic SF Comp A	3 part(s)
Jotamastic SF Comp B	1 part(s)

WINTER GRADE

Jotamastic SF Comp A	2.2 part(s)
Jotamastic SF Wintergrade Comp B	1 part(s)

Thinner/Cleaning solvent

Thinner: Jotun Thinner No. 17

Guiding data for airless spray

Nozzle tip (inch/1000):	19-25
Pressure at nozzle (minimum):	150 bar/2100 psi

Drying and Curing time

Substrate temperature	5 °C	10 °C	15 °C	23 °C	40 °C
STANDARD GRADE					
Surface (touch) dry			15 h	10 h	5 h
Walk-on-dry			52 h	26 h	10.5 h
Dry to over coat, minimum			52 h	26 h	10.5 h
Dried/cured for service			28 d	14 d	7 d
WINTER GRADE					
Surface (touch) dry	28 h	15 h	10 h	8 h	
Walk-on-dry	53 h	23 h	18 h	15 h	
Dry to over coat, minimum	53 h	23 h	18 h	15 h	
Dried/cured for service	21 d	14 d	7 d	5 d	

For maximum overcoating intervals, refer to the Application Guide (AG) for this product.

Drying and curing times are determined under controlled temperatures and relative humidity below 85 %, and at average of the DFT range for the product.

Surface (touch) dry: The state of drying when slight pressure with a finger does not leave an imprint or reveal tackiness.

Walk-on-dry: Minimum time before the coating can tolerate normal foot traffic without permanent marks, imprints or other physical damage.

Dry to over coat, minimum: The recommended shortest time before the next coat can be applied.

Dried/cured for service: Minimum time before the coating can be permanently exposed to the intended environment/medium.

Induction time and Pot life

Paint temperature **23 °C**

STANDARD GRADE

Pot life 1 h

WINTER GRADE

Pot life 1 h

Heat resistance

	Temperature	
	Continuous	Peak
Dry, atmospheric	120 °C	-
Immersed, sea water	50 °C	60 °C

Peak temperature duration max. 1 hour.

The temperatures listed relate to retention of protective properties. Aesthetic properties may suffer at these temperatures.

Note that the coating will be resistant to various immersion temperatures depending on the specific chemical and whether immersion is constant or intermittent. Heat resistance is influenced by the total coating system. If used as part of a system, ensure all coatings in the system have similar heat resistance.

Product compatibility

Depending on the actual exposure of the coating system, various primers and topcoats can be used in combination with this product. Some examples are shown below. Contact Jotun for specific system recommendation.

Previous coat: epoxy shop primer, inorganic zinc silicate shop primer, zinc epoxy, epoxy, epoxy mastic, inorganic zinc silicate
Subsequent coat: polyurethane, epoxy, acrylic, vinyl epoxy

Packaging (typical)

	Volume (litres)	Size of containers (litres)
Jotamastic SF Comp A	11	20
Jotamastic SF Comp B	3.67	5
Jotamastic SF Wintergrade Comp B	5	5

The volume stated is for factory made colours. Note that local variants in pack size and filled volumes can vary due to local regulations.

Storage

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf life at 23 °C

Jotamastic SF Comp A	18 month(s)
Jotamastic SF Comp B	12 month(s)
Jotamastic SF Wintergrade Comp B	12 month(s)

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Jotun's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Jotun representative for approval before commencing the work.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Do not inhale spray mist. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

Colour variation

When applicable, products primarily meant for use as primers or antifoulings may have slight colour variations from batch to batch. Such products and epoxy based products used as a finish coat may chalk when exposed to sunlight and weathering.

Colour and gloss retention on topcoats/finish coats may vary depending on type of colour, exposure environment such as temperature, UV intensity etc., application quality and generic type of paint. Contact your local Jotun office for further information.

Disclaimer

Technical Data Sheet

Jotamastic SF



The information in this document is given to the best of Jotun's knowledge, based on laboratory testing and practical experience. Jotun's products are considered as semi-finished goods and as such, products are often used under conditions beyond Jotun's control. Jotun cannot guarantee anything but the quality of the product itself. Minor product variations may be implemented in order to comply with local requirements. Jotun reserves the right to change the given data without further notice.

Users should always consult Jotun for specific guidance on the general suitability of this product for their needs and specific application practices.

If there is any inconsistency between different language issues of this document, the English (United Kingdom) version will prevail.
