



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

MAPECRETE LI HARDENER

Surface treatment in liquid form with a consolidating effect for new or old concrete floors and concrete surfaces with a dry-shake hardener finishing



DESCRIPTION

Mapecrete LI Hardener is a water solution of modified lithium silicates for treating the surface of cementitious substrates. It penetrates into the porosity and chemically reacts with the free lime in the cementitious substrate to form a dense microstructure which is chemically durable and resistant to abrasion. After polishing, floors treated with **Mapecrete LI Hardener** are shiny, dust-repellent, more resistant to staining and efflorescence and easy to clean.

WHERE TO USE

Mapecrete LI Hardener is suitable for new or old industrial and civil cementitious floors. It has the capacity of closing the porosity of the cementitious paste and, therefore, increasing the strength of the surface of the floor. This product is suitable for application on old floors to bring back shine, easy cleanability and strength to the surfaces treated.

Mapecrete LI Hardener increases the durability of the floor through the beneficial effect of the lithium salts against the “pop-out” aggregate alkali reaction affecting many floors, due to the effect of reactive aggregates. Beyond better mechanical characteristics, cementitious floors treated with **Mapecrete LI Hardener** are more resistant to aesthetic defects, such as efflorescence and various types of stains.

Some application examples

- Surface consolidation of industrial and civil floors (warehouses, shopping centres, car-parks, garages, craft workshops, etc.) made from concrete and flooring with cementitious dry-shake.
- Surface protection of cementitious floors to increase their resistance to abrasion, scratches and aesthetic defects.
- Final surface treatment after polishing concrete flooring.
- Dust-repellent treatment for industrial and civil floors.

TECHNICAL CHARACTERISTICS

Mapecrete LI Hardener is an inorganic liquid which penetrates superficially into the porosity of cementitious materials and reacts with the lime which is normally produced during the hydration phase of the cement, to form highly-resistant, non-soluble hydrate silicates which increase the density and strength of the cementitious paste.

Mapecrete LI Hardener has been developed in MAPEI R&D laboratories. It is not a film-forming product and, therefore, does not form a continuous layer on the surfaces treated. As a result, it is not subject to scratching and/or detachment.

Mapecrete LI Hardener is a solution of modified lithium silicates which are resistant to UV rays, thus suitable for application on both internal and external surfaces.

Mapecrete LI Hardener is made with lithium silicates which penetrate more efficiently than other silicates (e.g. sodium and potassium); this grants an effective protection against the destructive reaction of reactive aggregates.

ADVANTAGES

- Non-filming treatment which chemically reacts with the substrate.
- Easy to use and apply.
- Penetrates superficially to form strong, mechanically and chemically-resistant, non-soluble composites.
- Improves resistance to abrasion.

- Reduces the formation of dust and keeps the floor cleaner.
- Improves the appearance of treated surfaces and makes them more shiny.
- Increases the durability of floors.
- Does not contain sodium or potassium which may provoke damaging alkali-aggregate reactions.
- Makes maintenance required on floors much easier.

RECOMMENDATIONS

- Do not apply **Mapecrete LI Hardener** on dusty, crumbling or flimsy substrates.
- Do not apply **Mapecrete LI Hardener** on dirty surfaces or on surfaces which are soaked with oily and/or greasy substances.
- Before applying **Mapecrete LI Hardener**, make sure the surfaces are evenly dry and that there is no stagnant water or puddles.

APPLICATION PROCEDURE

Mapecrete LI Hardener may be applied just 2-3 days after casting the polished concrete or finished with dry-shakes such as products of the **Mapetop N** products range, and after cutting the joints where required. If the product is applied on surfaces which are already cured, the treatment may be carried out immediately.

Concrete surfaces including those with a dry-shake hardener such as **Mapetop N** products range or other cementitious products must be sound, perfectly clean, dry and free of all traces of dust, film-forming anti-evaporation products, grease, oil and any other substance or material which could prevent the consolidating liquid from penetrating.

Mapecrete LI Hardener may be applied by spraying it on the surface to be treated with a low pressure pump or poured directly on the floor and then immediately spread out in an even coat. In both cases, the part of the floor treated must be kept constantly wet for at least 20-30 minutes with **Mapecrete LI Hardener** to allow it to penetrate into the substrate. During this phase, it is very important that there are no dry and wet patches on the surface, for the better results of the treatment.

At the end of the phase when the surface is kept constantly wet any excess liquid must be removed manually or with suitable mechanical means and the treated surface must be dried and polished.

After completing the application and drying phases, we recommend waiting until the following day before stepping on the surface, even if the consolidating effect of the product takes place during the next days.

CLEANING

Tools used to prepare and apply **Mapecrete LI Hardener** may be cleaned quite simply with water. Once hardened, the product may only be removed using mechanical means.

CONSUMPTION

0.2-0.4 kg/m² according to weather conditions and the level of porosity and absorbency of concrete.

PACKAGING

25 kg plastic drums

STORAGE

Mapecrete LI Hardener may be stored for up to 12 months in its original packaging in a dry area at a temperature between +5°C and +40°C. Protect from frost.

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Instructions for the safe use of our products can be found on the latest version of the Safety Data Sheet, available from our website www.mapei.com.

PRODUCT FOR PROFESSIONAL USE.

TECHNICAL DATA (typical values)

PRODUCT IDENTITY	
Consistency:	liquid
Colour:	transparent

Density (g/cm ³):	1.1
Ion chloride content - minimum requirement ≤ 0.05% – according to EN 1015-17 (%):	≤ 0.05
pH - ISO 4316:	11

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation. The most up-to-date TDS can be downloaded from our website www.mapei.com.

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

571-6-2022-gb

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

