



New Guard Coatings Group

A global reputation to protect.

The information herewith is given with the best of New Guard Coatings Group knowledge.

Rights are reserved to change and update the data without notice.

This information is not exhaustive and it is the user's responsibility to ensure that this data sheet is the most current by contacting their local New Guard Coatings Group branch prior to using the coating/product.

www.newguardcoatings.com

NORTH • SOUTH EAST • MIDLANDS • NORTH WEST • HULL • SCOTLAND

MAPEFLEX E- PU 30 NS

Two-component, high-strength, epoxy-polyurethane sealant with high modulus of elasticity



WHERE TO USE

- Sealing vertical, sloping and horizontal joints, in exterior and interior also use subject to high mechanical stress.
- Abrasion resistant sealing of joints in industrial floors subject to heavy traffic, both in interior and exterior.
- Sealing joints where a thixotropic, resistant to mechanical stress and to chemicals, water and vapor proof product is required.
- Sealing floor-wall fillet joint.
- Sealing joints in rubber and PVC floors.
- Sealing joints in ceramic floors subject to heavy traffic, both pedestrian and vehicular, such as supermarkets, warehouses, production areas, sidewalks, walkways, arcades and squares.
- Sealing distribution joints in concrete floors, infrastructures and industrial buildings.
- Flexible sealing around machine bases in industries.
- Flexible sealing of pipe-work systems, drainage systems and manholes.

TECHNICAL CHARACTERISTICS

Mapeflex E-PU 30 NS is a two-component, thixotropic sealant made up of a epoxy-polyurethane polymer that does not contain free isocyanates (component A) and a special hardener (component B). The two components must be mixed together thoroughly to obtain a uniform coloured, thixotropic paste that is easy to apply with a flat trowel.

Mapeflex E-PU 30 NS can be used both on horizontal and vertical surfaces.

After hardening by chemical reaction alone, which takes place in about 24 hours without shrinkage, **Mapeflex E-PU 30 NS** becomes a flexible elastomer, resistant to water and slightly acidic or basic chemicals, with abrasion and friction (both sliding and rolling) resistant properties.

Mapeflex E-PU 30 NS bonds well on all the substrates that are commonly used in building. The application of a specific adhesives primer always increases the bonding properties and durability of the sealing, in particular under severe conditions.

The resistance of **Mapeflex E-PU 30 NS** to chemicals is good; however, due to the variety of products and working conditions under which it can be used, it is necessary to carry out preliminary tests in cases of doubt.

After complete polymerization **Mapeflex E-PU 30 NS** can be painted over with suitable elastomeric paints. In case the product needs to be painted over, it is recommended to apply the elastomeric paint in a suitable thickness, in order to avoid cracks on the surface of the paint layer due to deformation of the underlying sealant. It is always recommended to carry out preliminary tests to check compatibility between sealant and elastomeric paint.

Mapeflex E-PU 30 NS withstands temperature between -30°C and +80°C.

RECOMMENDATIONS

- Do not use on damp surfaces or surfaces subject to rising damp from underground.
- Do not use the product if the concrete is not completely cured, that is until shrinkage is completed.
- **Mapeflex E-PU 30 NS** is able to withstand working elongation that does not exceed 10%, therefore it is necessary that the joints have an average width at least 10 times greater than the sum of compression/traction movements expected. If this

condition cannot be respected, it is recommended to use a sealant with more extended working elongation (for ex. 20%, 25%...) or to enlarge the width of the joint (please contact beforehand our Technical Service).

- It is recommended not to seal the joint when its width is at the maximum or minimum level due to the high or low temperature of the substrate (for ex. summer/winter, day/night): if possible, seal the joint when its width is between the maximum and minimum level measured on site.
- Do not use on bituminous surfaces where the bleeding of oil may be present.
- The colour of the product may change if it is exposed to UV rays. This may happen in particular with light colours. However, this phenomenon does not affect the performance of the product.
- Do not apply **Mapeflex E-PU 30 NS** if the temperature is lower than +5°C.

APPLICATION PROCEDURE

Preparation of the surface to be sealed

The sealant can carry out its sealing function well and last in time only if the expansion joints are correctly sized. Always check that the average width of the joint is at least 10 times greater than the maximum movement expected. Accurately clean the surface of the joint using suitable manual or mechanic tools, with or without water, to remove any loose, detached part such as dust defoaming agents, cement laitance, hardened cement slurry and dirt in general.

Before sealing, make sure the joint is perfectly dry.

On the joint edges apply **Primer SN** or **Primer MF**, solvent-free, two-component epoxy primers.

To regulate the depth of the sealant and to avoid **Mapeflex E-PU 30 NS** sticking to the bottom of the joint, insert **Mapefoam**, expanded polyurethane flexible cord, with a diameter 10-20% larger than the maximum width of the joint to be sealed.

Insert the **Mapefoam** cord in the joint using a suitable tool. This operation enables also to regulate the depth of the sealant and to obtain a material section that respects the proportions indicated in the table below:

WIDTH OF JOINT	DEPTH OF SEALANT
up to 10 mm	same as width
from 11 to 20 mm	10 mm in all cases
more than 20 mm	half the width

To leave an attractive finish, we recommend using a masking tape along the edges of the joints, which must be removed immediately after smoothing off **Mapeflex E-PU 30 NS**.

Seal the joint only once the primer is dry to the touch (1-12 hours depending on the temperature) and in any case within 24 hours after its application. Before sealing the joint, make sure that it is clean and dry.

Preparation of the product

The two components (A and B) of **Mapeflex E-PU 30 NS** are supplied pre-dosed and must be completely and carefully mixed together until a uniform coloured, thixotropic paste is obtained.

Open the lid of the container and remove the bottle containing component B (liquid), shake it in order to homogenise it. Pour component B into component A (paste) and mix them together for few minutes with a low speed drill, avoiding air-entraining.

In case **Mapeflex E-PU 30 NS** needs to be coloured on site using **Mapecolor Paste** colouring pastes, they need to homogenise and dispersed in component A before mixing it with component B.

Avoid partial quantities. If necessary, dose the components by weight, considering that the mix ratio of component A and component B is 93 : 7.

Setting time and pot life are directly linked to the temperature of the environment: at +23°C they are approx. 40 minutes.

Application of the product

Immediately after having mixed the two components, seal the joint (after having prepared it as described above) using a small gauging trowel in order to apply the product by pressing it against the walls of the joint.

As an alternative, **Mapei Gun 600 PRO**, professional, manual tubular extrusion gun, can be used. The gun must be filled with the mixed product. **Mapeflex E-PU 30 NS** must be extruded directly in the joint.

Press and smooth over the surface with a clean trowel. Make sure that the trowel is wetted with a soap and water solution.

Remove the excess of **Mapeflex E-PU 30 NS** and finish its still fresh surface with a clean trowel or a sponge slightly moistened with a water and soap solution.

CLEANING

Mapeflex E-PU 30 NS can be removed while still fresh from surfaces, tools and clothes with toluol or ethyl alcohol. Once hardened, it can be removed only mechanically or with **Pulicol 2000**.

CONSUMPTION

Consumption depends on the size of the joint.
 The density of **Mapeflex E-PU 30 NS** is 1.45 g/cm³.
 The approximative consumption of the different possible sections is indicated in the table below.

width of joint (mm)	5	10	15	20	25	30	35	40
depth of sealant (mm)	5	10	10	10	12.5	15	17.5	20
Mapefoam Ø mm	6	15	20	25	30	40	40	2 x 20
Consumption of sealant (kg/m)*	0.04	0.15	0.22	0.29	0.45	0.65	0.89	1.16
Meters of sealant per 5 kg packaging	138	34	23	17	11	8	6	4
Consumption of Primer MF or Primer SN (kg/m/l)*	0.004	0.015	0.022	0.029	0.045	0.065	0.089	0.116

* theoretical consumption with no product waste

COLOURS

Mapeflex E-PU 30 NS is available in 113 grey and neutral, that can be used together with **Mapecolor Paste** for customised colours.
 Special colours are available upon request in min. quantities of 1000 kg.

PACKAGING

Mapeflex E-PU 30 NS is available in 5 kg units (component A = 4.65 kg + component B = 0.35 kg).

STORAGE

Mapeflex E-PU 30 NS is stable for 2 years if stored in a dry place at a temperature between +10°C and +35°C

SAFETY INSTRUCTIONS FOR PREPARATION AND APPLICATION

Mapeflex E-PU 30 NS part A is irritant for the skin and eyes. Both part A and B can cause sensitization if they come in contact with the skin of those predisposed. Furthermore, part B may cause irreversible damage if used for lengthy periods. It is corrosive and can cause burns and damage to eyes. The product contains low molecular weight epoxy resins that may cause sensitisation if cross-contamination occurs with other epoxy compounds.

During use wear protective clothes, gloves safety goggles, and a safety mask to protect the respiratory tract, and work only in well-ventilated areas. If the product comes in contact with the eyes or skin wash immediately with plenty of water and seek medical attention.

We advise against the use of pregnant women.

Furthermore, **Mapeflex E-PU 30 NS** component A and B are dangerous for aquatic life, do not dispose of them in the environment.

For further and complete information about the safe use of our product please refer to the latest version of our Safety Data Sheet.

RESTRICTED TO PROFESSIONAL USERS.

TECHNICAL DATA (typical values)		
PRODUCT IDENTITY		
	component A	component B
Consistency:	thick paste	fluid liquid
Colour:	white	straw yellow

Density (g/cm ³):	1.45	0.95
Dry solids content (%):	96	100
Brookfield viscosity at +23°C (mPa·s):	800,000 (rotor F - 5 revs)	250 (rotor F - 5 revs)
Mixing ratio:	93	7
APPLICATION DATA		
Consistency of the mix:	thixotropic paste	
Density of the mix (kg/dm ³):	1.45	
Pot life of the mix (workability):	40 minutes	
Application temperature:	from +5°C to +40°C	
Initial setting time:	8 hours	
Final setting time:	9 hours	
Set to light foot traffic:	24-36 hours	
Final hardening:	7 days	
Shore A hardness:	60	
Tensile strength (ISO 37):	2.2 N/mm ²	
Elongation at break (ISO 37):	125%	
In service temperature:	from -30°C to +80°C	
Maximum movement allowed in operation:	10%	

Values referred to 113 grey

WARNING

Although the technical details and recommendations contained in this product data sheet correspond to the best of our knowledge and experience, all the above information must, in every case, be taken as merely indicative and subject to confirmation after long-term practical application; for this reason, anyone who intends to use the product must ensure beforehand that it is suitable for the envisaged application. In every case, the user alone is fully responsible for any consequences deriving from the use of the product.

Please refer to the current version of the Technical Data Sheet, available from our website www.mapei.com

LEGAL NOTICE

The contents of this Technical Data Sheet ("TDS") may be copied into another project-related document, but the resulting document shall not supplement or replace requirements per the TDS in force at the time of the MAPEI product installation.

The most up-to-date TDS can be downloaded from our website www.mapei.com.

ANY ALTERATION TO THE WORDING OR REQUIREMENTS CONTAINED OR DERIVED FROM THIS TDS EXCLUDES THE RESPONSIBILITY OF MAPEI.

8110-9-2019-en

Any reproduction of texts, photos and illustrations published here is prohibited and subject to prosecution

